# TÜRBİN VE SİRKÜLASYON YAĞI SERIES

High-Quality Turbine Oil

## **Description**

High quality turbine oil with long service life, produced with special additives and high qualified base oils.

# **Applications**

It can be successfully used in gas, vapor and hydraulic turbines, reciprocating air compressors, medium pressure hydraulic systems, vacuum pumps and roller and journal bearings.

#### **Benefits**

- Maintains its viscosity at low temperatures and continues to flow. Likewise it provides efficient lubrication at elevated temperatures.
- Ensures efficient operation by preventing deposit formation.
- Prevents rust and wear by forming film layer on metallic surfaces.
- Prevents polishing of the turbine system bearings, due to its high resistance to oxidation and forming residue formed by oxidation and maintains its viscosity.
- Provides protection perfectly for bearings and gears due its excellent antiwear characteristics.
- Removes the water content from systems due to its high water separation characteristic.
- Protects turbines, gears and recirculated bearing lubrication systems against corrosive effects formed by ambient conditions.
- Prevents foaming due to its high air release characteristic.
- Prevents pressure surge pump during cold start due to its stable fluidity at low temperatures.
- Ensures wide range of application for corrosive environments like iron and steel, refinery, fertilizer and sugar processing industries.

### **Performance**

DIN 51515 (R+0), BS 489

# Typical Specifications\*

| ISO Viscosity Grade      |            | 22    | 32    | 46    | 68    | 100   | 150   | 220   |
|--------------------------|------------|-------|-------|-------|-------|-------|-------|-------|
| Density, 15 °C, kg/liter | ASTM D4052 | 0,860 | 0,873 | 0,878 | 0,883 | 0,886 | 0,891 | 0,895 |
| Flash Point, COC, °C     | ASTM D92   | 190   | 216   | 234   | 238   | 250   | 270   | 286   |
| Viscosity, 40 °C, mm²/s  | ASTM D445  | 22    | 32    | 46    | 68    | 100   | 150   | 220   |
| Viscosity, 100 °C, mm²/s |            | 4,50  | 5,40  | 6,70  | 8,60  | 11,10 | 14,40 | 18,50 |
| Viscosity Index          | ASTM D2270 | 100   | 101   | 98    | 97    | 95    | 93    | 93    |
| Pour Point, °C           | ASTM D97   | -18   | -21   | -18   | -18   | -9    | -6    | -6    |

<sup>\*</sup> Values shown may differ between productions.



